

(Translation)

Official Emblem

No. 0307/ **17607**

To Forconthai Sealant Co., Ltd.

The Department of Science Service presents the test report for the sample named "FROCON - D WALL PUTTY" Laboratory No. L65/08432.1 as the total of 1 sample with reference to the request No. L65/08432 dated 5 October 2022.

Enclosed herewith the following result avails for your acknowledgement.

Official Seal Affixed
Department of Science Service
14 November 2022

Division of Engineering Materials

Tel. 0 2201 7130

Fax. 0 2201 7127

E-mail : physics@dss.go.th





TEST REPORT

Sample's name

FROCON - D WALL PUTTY

Mark / Brand

-

Laboratory No.

L65/08432.1

Test Results

Peel strength, N/25 mm in width

- Mortar

20.5

- Aluminium

40.3

Tack free time, minutes

15

Specific Gravity

1.75



Certified correct translation

(Mr.Kanit Tapasa)

Director, Division of Engineering Materials

This report is only valid for the sample received. The above statement is not intended for advertising purposes and shall not be partially reproduced or manifested without the written permission from the Department of Science Service.

Department of Science Service, Ministry of Higher Education Science Research and Innovation


Rama VI Road, Ratchathewi, Bangkok 10400, Thailand

Laboratory No. L65/08432.1

Customer's name Forconthai Sealant Co., Ltd.

Customer's address 100/58 Moo 1, Samkhok-Pathamthani Road, Samkhok, Pathumthani
12160

Sample's description White viscous liquid packed in a plastic bucket



Test date 10 October – 9 November 2022

Test method
1. Peel strength : ASTM C794-15a
2. Tack free time : ASTM C679-15
3. Specific gravity : ASTM D1475-13

Approved by
(Sgd.) Kartpan Sakulkaew
(Mr. Kartpan Sakulkaew)
Scientist, Senior Professional Level

Reported by
(Sgd.) Pawadee Sriyota
(Miss Pawadee Sriyota)
Scientist



Director, Division of Engineering Materials

This report is only valid for the sample received. The above statement is not intended for advertising purposes and shall not be partially reproduced or manifested without the written permission from the Department of Science Service.

Department of Science Service, Ministry of Higher Education Science Research and Innovation
Rama VI Road, Ratchathewi, Bangkok 10400, Thailand